

CHEMICAL RESISTANCE CHART

This Chemical Resistance Chart is intended to provide general information about the reactions of different glove materials to the chemicals listed. Variability in glove thickness, chemical concentration, temperature and length of exposure to chemicals will affect the performance.

Warning: Protective gloves and other protective apparel selection must be based on the user's assessment of the workplace hazards. Gloves and Apparel materials do not provide unlimited protection against all chemicals. It is the user's responsibility to determine before use that the Glove and Apparel will resist permeation and degradation by the chemicals (including chemical mixtures) in the environment of intended use. Failure by the user to select the correct protective gloves can result in injury, sickness or death.

KEY: P = Poor F = Fair G = Good E = Excellent NR = Not Recommended

Chemical	Neoprene	Nitrile	Latex	PVC	Chemical	Neoprene	Nitrile	Latex	PVC
Acetaldehyde	E	P	F	NR	Kerosene	E	E	P	F
Acetic Acid	E	G	G	F	Lactic Acid	E	E	E	E
Acetone	G	NR	G	NR	Lauric Acid	E	E	G	F
Acetonitrile	F	NR	F	NR	Linoleic Acid	E	E	P	G
Ammonium Hydroxide<30%	E	E	G	E	Linseed Oil	E	E	P	E
Amyl Acetate	NR	E	F	P	Maleic Acid	E	E	P	G
Amyl Alcohol	P	G	G	NR	Methyl Acetate	G	P	P	NR
Aniline	G	NR	P	F	Methyl Alcohol	E	E	E	G
Animal Fats	E	E	P	G	Methylamine	G	E	E	E
Battery Acids	E	E	G	E	Methyl Bromide	NR	NR	NR	NR
Benzaldehyde	NR	NR	F	NR	Methylene Chloride	NR	NR	NR	NR
Benzene	NR	P	NR	NR	Methyl Cellulose	E	F	P	-
Benzoyl Chloride	NR	NR	P	NR	Methyl Ethyl Ketone (MEK)	G	NR	G	NR
Butane	F	E	P	P	Methylisobutyl Ketone	NR	P	F	NR
Butyl Acetate	NR	F	P	NR	Methyl Methacrylate	NR	P	P	NR
Butyl Alcohol	E	P	E	G	Mineral Oil	E	E	P	F
Butyl Cellulose*	E	E	E	NR	Mineral Spirits	G	E	NR	F
Carbon Acid	E	P	P	G	Monoethanolamine	E	E	G	E
Carbon Disulfide	NR	NR	NR	NR	Morpholine	P	NR	G	NR
Carbon Tetrachloride	P	G	NR	NR	Muriatic Acids	E	G	G	G
Castor Oil	E	E	E	E	Naptha V.M & P.	G	E	NR	P
Cellosolve Acetate	E	G	G	NR	Nitric Acid <30%	E	P	G	G
Cellosolve Solvent	E	G	E	NR	Nitrile Acid 70%	G	NR	F	F
Chlorobenzene	NR	NR	NR	NR	Nitrile Acid Red Fuming	NR	NR	P	P
Chloroform	F	F	NR	NR	Nitrile Acid White Fuming	NR	NR	P	P
Chloronaphalens	NR	F	NR	NR	Nitrobenzene	NR	NR	P	NR
Chloroethene VG	NR	F	NR	P	Nitromethane	E	F	G	P
Chromic Acid	F	F	NR	G	Nitropropane	G	NR	E	NR
Citric Acid	E	E	E	E	Octyl Alcohol	E	E	G	F
Cottonseed Oil	E	E	P	G	Oleic Acid	E	E	P	F
Cresols	G	G	P	F	Paint Remover	G	G	F	P
Cutting Oil	E	E	F	P	Palmitic Acid	E	G	G	G
Cyclohexane	F	E	P	P	Pentachlorophenol	E	E	P	F
Cyclohexanol	E	E	P	G	Pentane	E	E	P	NR
Dibutyl Phthalate	F	G	P	G	Perchloric Acid 60%	E	E	P	E
Diethylamine	P	F	NR	NR	Potassium Hydroxide <50%*	E	G	E	E
Di-Isobutyl Ketone	P	E	P	P	Printing Ink	G	E	G	F
Dimethyl Formamide (DMF)	G	NR	E	NR	Propyl Acetate	P	F	P	NR
Dimethyl Sulfoxide (DMSO)	E	E	E	NR	Propyl Alcohol	E	E	E	F
Dioctyl Phthalate (DOP)	G	G	P	NR	Perchloroethylene	NR	G	NR	NR
Dioxane	NR	NR	NR	NR	Phenol	E	NR	G	G
Ethyl Acetate	F	NR	P	NR	Phosphoric Acid*	E	E	G	G
Ethyl Alcohol	E	E	E	G	Picric Acid	E	E	G	E
Ethylene Dichloride	NR	NR	P	NR	Propylene Oxide	NR	NR	P	NR
Ethylene Glycol	E	E	E	E	Rubber Solvent	G	E	NR	NR
Ethyl Ether	E	E	NR	NR	Sodium Hydroxide <50%	E	G	E	G
Ethylene Trichloride	P	P	P	NR	Stoddard Solvent	E	E	P	NR
Formaldehyde	E	E	E	E	Styrene*	NR	NR	NR	NR
Formic Acid	E	F	E	E	Sulfuric Acid 95%	F	G	NR	NR
Freon	G	F	NR	NR	Tannic Acid	E	E	E	E
Furfural	G	NR	E	NR	Tetrahydrofuran (THF)	NR	NR	NR	NR
Gasoline	P	E	NR	P	Toluene	P	G	NR	NR
Glycerine	E	E	E	E	Toluene Di-Isocyanate (TDI)	NR	NR	P	P
Hexane	E	E	NR	NR	Trichlorethylene (TCE)	P	G	NR	NR
Hydraulic Fluid Petro. Based	F	E	P	G	Tricrestyl Phosphosphate (TCP)	F	E	G	F
Hydraulic Fluid Easter Based	P	P	P	P	Triethanolamine 85% (TEA)	E	E	G	E
Hydrazine 65%	E	E	G	E	Tung Oil	E	E	NR	F
Hydrochloric Acid*	G	E	E	E	Turbine Oil	E	G	P	F
Hydrofluoric Acid	G	E	E	E	Turpentine	G	E	P	P
Hydrogen Peroxide	E	E	E	E	Vegetable Oil	E	E	P	F
Hydroquinone	G	E	E	E	Xylene	P	G	NR	NR
Isobutyl Alcohol	E	E	E	F					
Iso-Octane	E	E	NR	P					
Isopropyl Alcohol*	E	E	E	G					